



## LABORATORY TEST REPORT

COMPOUND: Sevrene<sup>®</sup> 3582-65A  
COLOR: N/A  
SPECIFICATION: GENERAL


Page 1 of 1

DATA REPRESENTS ACTUAL LABORATORY TESTS

### PHYSICAL PROPERTIES

### RESULTS

Durometer, Shore A 15 sec delay ISO 868	65
Specific Gravity, ISO 1183	0.98
Tensile Strength, ISO 37, MPa	8.0
Ultimate Elongation ISO 37, %	754
Tensile Modulus, ISO 37, 100% MPa	2.0
Tear Strength, ISO 34, kN/m	31

Approved by: 

\* Test is outside our scope of accreditation.

\*\* This test was performed by a subcontracted accredited testing laboratory.

\*\*\* This test was performed at supplier's biological laboratory.

\\Vc\p1\data\SHARED\LabData\2008\296\_Prelim\_Sevrene3582\_65A\_General.doc

All tests are performed once.

This report is not to be reproduced except in full.