


LABORATORY TEST REPORT

COMPOUND: Uravin™ 901-65FR
 COLOR: N/A
 SPECIFICATION: GENERAL

Test Method	Results
Hardness, Shore A, ASTM D2240	
Instant	69
15 second delay	63
Specific Gravity, ASTM D792	1.22
Tensile Strength, psi, Die C, ASTM D412	1441
100% Modulus, psi	879
300% Modulus, psi	1227
Elongation, %	434
Tear Strength, lbs./in., ASTM D1004	92
Melt Index, 177°C, 3.7 kg	28
Cold Temperature Flex. -40°C	Pass
Taber Abrasion, 1000 cycles, CS-10 Wheel, %	0.014

Approved by: 

* Test is outside our scope of accreditation.
 ** This test was performed by a subcontracted accredited testing laboratory. All tests are performed once.
 *** This test was performed at supplier's biological laboratory. This report is not to be reproduced except in full.

\\Vcfp1\data\SHARED\LabData\2009\381_Uravin901-65FR General.doc