




LABORATORY TEST REPORT

COMPOUND: Sevrene® 4000-35A
COLOR: N/A
SPECIFICATION: GENERAL

PAGE: 1 of 1

DATA REPRESENTS ACTUAL LABORATORY TESTS

Test Method	Results
Specific Gravity, ISO 1183	1.07
Hardness, ISO 868, Shore A, 15 second delay	39
Tensile Strength, ISO 37, 500 mm/min.	3.56 MPa
% Elongation at break, ISO 37, 500 mm/min.	559%
Tear Strength, ISO 34-1B, 500 mm/min.	14.9 kN/m
Melt Flow, ISO 1133, 230°C, 2.16 Kg load	5 grams/10 min.

Approved by: 

* Test is outside our scope of accreditation.

** This test was performed by a subcontracted accredited testing laboratory.

*** This test was performed at supplier's biological laboratory.

O:\2011\499_Sevrene4000-35A_General.doc

All tests are performed once.

This report is not to be reproduced except in full.